

## **1422A TYVEK® CONTINUOUS FORM TUBING**



## TYPICAL APPLICATION & CHARACTERISTICS:

Recommended for Steam Sterilization of Pharmaceutical Production Equipment

- Cut to desired length size flexibility
- Cost Effective
- Tyvek® on both sides for maximum steam penetration during sterilization
- Minimizes the use of autoclave tape
- Fast and consistent for equipment preparation area
- Creates strong seals when heat sealed
- Hydrophobic
- Resists tearing and punctures
- Superior microbial barrier
- Lint-Free
- Manufactured and packaged in ISO certified cleanrooms
- Certificates of Conformance sent with all shipments
- Made in USA



## **1422A TYVEK® CONTINUOUS FORM TUBING**



## **MATERIAL SPECIFICATIONS:**

PROPERTY	UNITS	TEST METHOD	TYPICAL VALUES 1422A TYVEK®
Seal Strength	N/mm	F-88	>.78
Basis Weight	g/m2	EN ISO 536	41
Total Thickness	μ	EN 20534	130
Air Permeability	S	ISO 5636-5	20
Water Vapor Permeability	G/M2/24 HR	ASTM 398	1700
Hydrostatic Head	cm h2o	ISO 811	120
Trapezoidal Tear MD/CD	N	ISO 9073-4	26.1/30.6
Linting Propensity	Rating	BS 6909 (Shirley Method 21)	Pass Rating: Excellent
Burst Resistance	kPa	ISO 2960 (50 cm2)	108
Puncture Resistance	N	EN 863	10.8
Melting Point	c°		135

_	<del></del>	
	KEYSTONE PART NUMBER	DIMENSIONS
	TUBT2A02	2"
	TUBT2A03	3"
	TUBT2A04	4"
TUBT2A05		5"
	TUBT2A06	6"
	TUBT2A08	8"
	TUBT2A10	10"
	TUBT2A12	12"
	TUBT2A15	15"
	TUBT2A16	16"
	TUBT2A24	24"
	TUBT2A28	28"
	TUBT2A30	30"
	TUBT2A40	40"

