

SINCE 1925

KEYSTONE

SAFETY ⇄ CLEANROOM PRODUCTS

PURECLEAN™

1421B TYVEK® AUTOCLAVE BAG WITH STEAM INDICATOR



PureClean™ Autoclave Bags are made from 1421B DuPont™ Tyvek®, which is a new grade of uncoated, untreated, flexible Tyvek® material. It has been specifically designed for pharmaceutical use in steam sterilization applications.

Keystone's PureClean™ Tyvek® material does not have a water soluble antistat agent applied to it during its manufacturing process.

- Uncoated Tyvek® on both sides for maximum breathability during sterilization without the chance of residue deposits on equipment, post sterilization
- Eliminates the need to cut material and the use of autoclave tape
- Fast and consistent for equipment preparation area
- Strong, sealed seams eliminate sewing threads and greatly reduce particulates
- Resists tearing and punctures
- Superior microbial barrier
- Manufactured and packaged in a certified ISO 6 cleanroom
- Made in the USA
- Certificates of Conformance sent with shipment

MATERIAL SPECIFICATIONS:

Property	Comparable standard test method	Units	Nominal value (range) Tyvek® 1421B
Preliminary product specifications (English units)			
Basis weight	ASTM D3776 ¹	oz/yd ²	1.22 [1.16–1.26]
Delamination	ASTMD2724 ²	lb _f	0.08 [>0.03]
Gurley Hill porosity	TAPPI T460 ³	sec/100 cc	20 [8–36]
Preliminary product specifications (metric units)			
Basis weight	ASTM D3776 ¹	g/m ²	41 [39–43]
Delamination	ASTMD2724 ²	N	0.36 [>0.13]
Gurley Hill porosity	TAPPI T460 ³	sec/100 cc	20 [8–36]

SINCE 1925

KEYSTONE

SAFETY ⇄ CLEANROOM PRODUCTS

PURECLEAN™

1421B TYVEK® AUTOCLAVE BAG WITH STEAM INDICATOR

Property (Continued)	Comparable standard test method	Units	Typical value Tyvek® 1421B
Preliminary miscellaneous properties (English units)			
Thickness	EN ISO 534 ¹	mils	6 (0.15mm)
Tensile strength, MD	EN ISO 1924-2 ²	lb /in	7.6
Tensile strength, CD	EN ISO 1924-2 ²	lb /in	6.4
Elmendorf tear, MD	ASTM D1424	lb _f	2.4
Elmendorf tear, CD	ASTM D1424	lb _f	1.9
Hydrostatic head	AATCC TM 127 ³	in H ₂ O	44
Elongation, MD	EN ISO 1924-2 ²	%	10
Elongation, CD	EN ISO 1924-2 ²	%	15
Puncture resistance	EN 863 ⁴	lb _f	2.7
Mullen burst	ISO 2758	psi	53
Bendsten air permeability	ISO 5636-3 ⁵	mL/min	741
Microbial barrier	ASTM F1608	LRV	~4

MD = machine direction; CD = cross direction

1. Surface 2 cm², pressure 50kPa.

2. Modified for speed, sample width 2.54 cm (1 inch).

3. Rate of use: 60 cm H₂O/min.

4. Modified for conditioning.

5. Electronic device.

Property	Comparable standard test method	Units	Typical value Tyvek® 1421B
Preliminary miscellaneous properties (metric units)			
Thickness	EN ISO 534 ¹	µm	152
Tensile strength, MD	EN ISO 1924-2 ²	N	34
Tensile strength, CD	EN ISO 1924-2 ²	N	28
Elmendorf tear, MD	ASTMD1424	N	10.6
Elmendorf tear, CD	ASTMD1424	N	8.5
Hydrostatic head	AATCC TM 127 ³	cm H ₂ O	112
Elongation, MD	EN ISO 1924-2 ²	%	10
Elongation, CD	EN ISO 1924-2 ²	%	15
Puncture resistance	EN 863 ⁴	N	12
Mullen burst	ISO 2758	kPa	365
Bendsten air permeability	ISO 5636-3 ⁵	mL/min	741
Microbial barrier	ASTM F1608	LRV	~4

MD = machine direction; CD = cross direction

1. Surface 2 cm², pressure 50kPa.

2. Modified for speed, sample width 2.54 cm (1 inch).

3. Rate of use: 60 cm H₂O/min.

4. Modified for conditioning.

5. Electronic device.

PURECLEAN™ 1421B TYVEK® AUTOCLAVE BAG WITH STEAM INDICATOR



KEYSTONE PART NUMBER	DIMENSIONS	KEYSTONE PART NUMBER	DIMENSIONS
6STK0205	2" x 5"	6STK1624	16" X 24"
6STK0404	4" X 4"	6STK1830	18" X 30"
6STK0409	4" x 9"	6STK2020	20" X 20"
6STK0416	4" x 16"	6STK2024	20" x 24"
6STK0820	8" x 20"	6STK2030	20" x 30"
6STK09-512	9.5" x 12"	6STK2040	20" x 40"
6STK1015	10" x 15"	6STK2224	22" x 24"
6STK1020	10" X 20"	6STK2424	24" x 24"
6STK1212	12" x 12"	6STK2436	24" x 36"
6STK1216	12" x 16"	6STK2448	24" x 48"
6STK1218	12" x 18"	6STK2844	28" x 44"
6STK1234	12" x 34"	6STK3036	30" X 36"
6STK1240	12" x 40"	6STK3636	36" x 36"
6STK1246	12" x 46"	6STK3648	36" X 48"
6STK1248	12" x 48"	6STK3660	36" x 60"
6STK1424	14" x 24"	6STK4848	48" x 48"